



## LNP\* Stat-loy\* Compound 93000LTH

Americas: COMMERCIAL

Also known as: LNP\* Stat-loy\* Compound 93000LTH

Product reorder name: 93000LTH

LNP\* Stat-Loy\* 93000LTH is a compound based on Acrylic resin featuring a permanent anti-static characteristic. Added features include: Transparent and Formulation Locked.

PICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	400	kgf/cm²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	7	%	ASTM D 638
Tensile Modulus, 5 mm/min	18200	kgf/cm²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	470	kgf/cm²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	14900	kgf/cm²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	68	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	66	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.15	-	ASTM D 792
ELECTRICAL			
Volume Resistivity	1.E+09 - 1.E+11	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+09 - 1.E+11	Ohm	ASTM D 257
Static Decay, 5000V to <50V	<1	< seconds	FTMS101B



(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the molume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

- (2) Only typical data for selection purposes. Not to be used for part or tool design.
  (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

- (3) This fathing is not interiored to consider the conditions.

  (4) Internal measurements according to UL standards.
  (5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mo shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

## Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BY, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com.and Are Available upon request. Although any information or recommendation contained herein is given in good fairly, seller makes no warranty or guaranties, express or implications. Except a selection of selections of sale selections of selections of selections of selections. Except a selection of selections of selections of selections of selections of selections. Except of any design incommendation selection of selections of selections of selections of selections of selections of selections of selections. Except of any design in selection of selections of

- \* LNP is a trademark of SABIC Innovative Plastics IP BV
- \* Stat-lov is a trademark of SABIC Innovative Plastics IP BV

© 1997-2011 SABIC Innovative Plastics Holding BV.All rights reserved





LNP\* Stat-loy\* Compound 93000LTH Americas: COMMERCIAL

广州华秀塑胶有限公司

(Sabic沙伯基础创新塑料 一级经销商) www.va-so.cn 联系电话: 020-82582555

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BY, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com.AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR RIMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR REFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

 $<sup>^{\</sup>ast}\,\mbox{LNP}$  is a trademark of SABIC Innovative Plastics IP BV

<sup>\*</sup> Stat-loy is a trademark of SABIC Innovative Plastics IP BV





## LNP\* Stat-loy\* Compound 93000LTH

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	70 - 80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05 - 0.1	%
Melt Temperature	200 - 210	°C
Front - Zone 3 Temperature	205 - 215	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	180 - 195	°C
Mold Temperature	10 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

广州华秀塑胶有限公司 (Sabic沙伯基础创新塑料 一级经销商) www.va-so.cn 联系电话: 020-82582555

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the m volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

- (2) Only typical data for selection purposes. Not to be used for part or tool design.
  (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire

- (3) This fating is not interface to reflect interface as personal processors.

  (4) Internal measurements according to UL standards.

  (5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

## Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BY, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com.AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR RIMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR REFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed Seller. No statement Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe B.V.

<sup>\*</sup> LNP is a trademark of SABIC Innovative Plastics IP BV

<sup>\*</sup> Stat-loy is a trademark of SABIC Innovative Plastics IP BV