



## LNP\* Stat-loy\* Compound A3000T

## **Europe-Africa-Middle East: COMMERCIAL**

Also known as: A-CLEAR

**Product Reorder Name: A3000T** 

LNP\* Stat-loy\* A3000T is a compound based on Acrylonitrile Butadiene Styrene resin. Added features of this material include: Antistat.

## **Property**

| TYPICAL PROPERTIES (1)                  |                 |       |              |
|---|-----------------|-------|--------------|
| MECHANICAL                              | Value           | Unit  | Standard     |
| Tensile Stress, break, 5 mm/min         | 28              | MPa   | ISO 527      |
| Tensile Strain, break, 5 mm/min         | >25             | %     | ISO 527      |
| Tensile Modulus, 1 mm/min               | 1300            | MPa   | ISO 527      |
| Flexural Stress, break, 2 mm/min        | 37              | MPa   | ISO 178      |
| Flexural Modulus, 2 mm/min              | 1200            | MPa   | ISO 178      |
| IMPACT                                  | Value           | Unit  | Standard     |
| Izod Impact, unnotched 80*10*4 +23°C    | NB              | kJ/m² | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C      | 15              | kJ/m² | ISO 180/1A   |
| THERMAL                                 | Value           | Unit  | Standard     |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm   | 69              | °C    | ISO 75/Af    |
| PHYSICAL                                | Value           | Unit  | Standard     |
| Mold Shrinkage on Tensile Bar, flow (2) | 0.6 - 0.8       | %     | SABIC Method |
| Density                                 | 1.07            | g/cm³ | ISO 1183     |
| ELECTRICAL                              | Value           | Unit  | Standard     |
| Surface Resistivity                     | 1.E+09 - 1.E+11 | Ohm   | ASTM D 257   |

Source GMD, last updated:10/24/2006

## **Processing**

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR (LOCAL SALES OFFICE) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer: All information, recommendation or advice given by SABIC Innovative Plastics, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC Innovative Plastics Company, its subsidiaries and affiliates

cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

- \* LNP is a trademark of the SABIC Innovative Plastics Company
- \* Stat-loy is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved